

# Potassium Titanyl Phosphate - KTP

---

Potassium Titanyl Phosphate (KTP or  $\text{KTiOPO}_4$ ) is a nonlinear optical material suitable for use in many optical systems. Its most popular application is as a frequency doubler utilizing the 1064nm output of a Nd:YAG laser. The conversion efficiency to 532nm is up to 60% at 250 MW /  $\text{cm}^2$ . KTP's properties also make it superior as an electro-optic modulator, optical parametric generation and optical waveguiding. SYNOPTICS has spent many years on the crystal growth and development of KTP.

## Applications

KTP's unique combination of properties, high nonlinear coefficients, high damage threshold, and the fact that it is non-hygroscopic as well, suit it to those laser systems applications requiring high power, high efficiency, and/or durability. It can be used in both commercial and military lasers including medical and laboratory systems, range-finders, designators and systems for use in the semiconductor industry. Any export or re-export of this product requires U.S. Government approval.

## Crystal Growth

SYNOPTICS' growth of KTP for nonlinear applications utilizes the hydrothermal process. In this technique crystals are grown in seeded aqueous solutions of KTP at elevated pressures and temperatures. Seed orientation makes use of the growth directions perpendicular to the (011) face. Typical crystal sizes of 15 x 20 x 40 mm are obtained using this technique.

# Crystal Structure

Structurally, Potassium Titanyl Phosphate (KTP) is orthorhombic and belongs to the acentric point group mm2. Its complicated structure is characterized by chains of TiO<sub>6</sub> octahedral linked at two corners by alternating long and short Ti-O bonds. The analysis of Zumsteg et al indicates that it is primarily these short Ti-O bonds that give rise to the large nonlinear optical effects observed in KTP. Some of the more useful physical properties of the material are given in *Table I*.

<b>Physical Chemical Properties</b>	
<b>Formula:</b>	KTiOPO <sub>4</sub>
<b>Crystal Structure:</b>	Orthorhombic, Space Group Pna 2 <sub>1</sub>
<b>Lattice Parameters:</b>	a = 12.81Å b = 6.404Å c = 10.616Å
<b>Melting Point:</b>	~ 1150°C with partial decomposition
<b>Mohs Hardness:</b>	~ 5
<b>Color:</b>	colorless
<b>Density (X-Ray):</b>	3.03 g / cm <sup>3</sup>
<b>Specific Heat:</b>	0.1737 cal / gm°C
<b>Thermal Conductivity:</b>	k <sub>1</sub> = 2.0, k <sub>2</sub> = 3.0, k <sub>3</sub> = 3.3 (x1 0 <sup>-2</sup> W / cm / °C)
<b>Absorption Loss @ 1.064 μm:</b>	< 1% / cm

<b>Nonlinear Properties</b>	
<b>Nonlinear Optical Coefficients (x 10<sup>12</sup> m / V):</b>	d <sub>31</sub> = 6.5, d <sub>32</sub> = 5.0, d <sub>33</sub> = 13.7, d <sub>24</sub> = 7.6, d <sub>15</sub> = 6.1
<b>Refractive Indices @ 1.064 μm:</b>	n <sub>x</sub> = 1.740, n <sub>y</sub> = 1.747, n <sub>z</sub> = 1.830
<b>Refractive Indices @ .532 μm:</b>	n <sub>x</sub> = 1.779, n <sub>y</sub> = 1.792, n <sub>z</sub> = 1.887
<b>Type Phase Matching:</b>	Type II
<b>Phase Matching Angle (@1.064 μm):</b>	24° to x in xy plane
<b>Spectral Bandwidth (Å - cm):</b>	5.6
<b>Angular Bandwidth (mrad - cm):</b>	15 - 68
<b>Temperature Bandwidth (°C - cm):</b>	25
<b>Walk-off Angle (mrad):</b>	1

## Potassium Titanyl Phosphate - KTP

### **Introduction**

Potassium Titanyl Phosphate (KTiOPO<sub>4</sub>'KTP) - was first synthesized in 1890 by L. Ouvarov but it wasn't until the 1970's that Zumsteg, Bierlein and Gier at E.I. DuPont identified the nonlinear optical properties of this crystal. These properties proved to be extremely desirable for several solid state laser applications. In the late 1970's, SYNOPTICS joined forces with DuPont to pursue the advanced development of this material. Since then, SYNOPTICS has spent many years developing the crystal growth and fabrication of KTP, and today, at our facility our fully equipped laboratories are capable of high volume hydrothermal growth, macro/micro-fabrication and active/passive testing with stringent in-house quality control.

### **Applications**

KTP's unique combination of properties (high nonlinear coefficients, high damage threshold and non-hygroscopicity) make it well suited for laser system applications requiring high power, high efficiency and/or durability. Commercial and military applications range from medical, industrial and laboratory systems to rangefinders, designators and systems used in the semi-conductor industry. Export and re-export of this product may require U.S. Government approval.

## Crystal Properties

### **Structural:**

KTP is orthorhombic in structure and belongs to the accentric point group mm2. Its complicated structure is characterized by chains of TiO<sub>6</sub> octahedra linked at two corners by alternating long and short Ti-O bonds that give rise to the large nonlinear optical effects observed in KTP. The constant growth rate of the hydrothermal process insures homogeneity throughout the crystal bulk.

### **Optical:**

KTP possesses optical properties that allow it to be used for both intra- and extra-cavity laser applications. It is optically transparent from 0.35  $\mu\text{m}$  to 3.5  $\mu\text{m}$ . The optical spectrum is structure-free except for traces of OH-absorption bands observed at 2.8  $\mu\text{m}$  and 3.8  $\mu\text{m}$ . Crystals with little or no scatter have been produced with very low strain. Damage thresholds have been measured well in excess of 1 GW/cm<sup>2</sup>. The refractive indices vary slowly with changes in wavelength and temperature.

### **Nonlinear Optical**

The nonlinear optical coefficients are comparable to those of Ba<sub>2</sub>NaNb<sub>5</sub>O<sub>15</sub> and KTP can be phase matched at 1.06  $\mu\text{m}$  using either Type I or Type II interactions. In Type II interactions, KTP has large angular and temperature bandwidths as well as high nonlinear coefficients and damage thresholds. It has a high conversion efficiency for second harmonic generation (SHG) of laser light with fundamental wavelengths between .994 and 2.5  $\mu\text{m}$ .

This material is also well suited for use as an optical parametric oscillator (OPO). KTP's wide tuning range and high conversion efficiencies mean that short crystals can be used in this application. Another application well suited for KTP is quasi phase matching (QPM). In this process z-oriented waveguides of KTP are periodically poled and pumped with diode lasers to generate blue to near UV wavelengths.\*

**Electro-Optical (E-O):**

KTP possesses E-O properties comparable to those of LiNbO<sub>3</sub> for bulk modulator applications with a figure of merit ( $n^7r^2/\epsilon$ ) of 3650 (pm/v)<sup>2</sup>. KTP is also a superior material for waveguide E-O modulators with a figure of merit ( $n^3r/\epsilon_{\text{eff}}$ ) of 17.3 pm/v. When these properties are coupled with KTP's high damage threshold, wide optical bandwidth (>15GHz), thermal and mechanical stability, the combination makes it a unique material for modulator applications.

\*Ref. "W.P. Risk and S.D. Lau, Opt. Lett., vol. 18, p. 272, 1993."

Specifications and information are subject to change without prior notice.  
© 2011 Northrop Grumman Corporation

---

1-704-588-2340 • FAX 704-588-2516  
1201 Continental Blvd., Charlotte, NC 28273  
[Email: STSynoptics.Sales@ngc.com](mailto:STSynoptics.Sales@ngc.com)  
[Website:www.as.northropgrumman.com/synoptics](http://www.as.northropgrumman.com/synoptics)

**NORTHROP  
GRUMMAN**   
SYNOPTICS